



US 20030056819A1

(19) **United States**(12) **Patent Application Publication** (10) Pub. No.: **US 2003/0056819 A1**

Imai et al.

(43) Pub. Date: **Mar. 27, 2003**(54) **THERMOELECTRIC MATERIAL AND
THERMOELECTRIC CONVERTING
ELEMENT USING THE SAME**(75) Inventors: **Hidetoshi Imai, Tokyo (JP); Yuichi
Shimakawa, Tokyo (JP); Takashi
Manako, Tokyo (JP); Yoshimi Kubo,
Tokyo (JP)**Correspondence Address:
**Paul J. Esatto, Jr.
Scully, Scott, Murphy & Presser
400 Garden City Plaza
Barden City, NY 11530 (US)**(73) Assignee: **NEC Corporation, Tokyo (JP)**(21) Appl. No.: **10/082,965**(22) Filed: **Feb. 25, 2002**(30) **Foreign Application Priority Data****Mar. 6, 2001 (JP) 2001-61811****Publication Classification**(51) Int. Cl.⁷ **C01B 17/20; H01L 35/12;
C01B 25/14; H01L 35/14**
(52) U.S. Cl. **136/239; 423/508; 423/511;
423/561.1; 136/236.1; 136/240**(57) **ABSTRACT**

Compounds are expressed by general formula of A_xBC_{2-y} where $0 \leq x \leq 2$ and $0 \leq y < 1$, and have CdTe analogous layer structures; A-site is occupied by at least one element selected from the group consisting of Li, Na, K, Rb, Cs, Mg, Ca, Sr, Ba, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Zn, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Cd, Hf, Ta, W, Re, Ir, Pt, Au, Sc, rare earth elements containing Y, B, Al, Ga, In, Tl, Sn, Pb and Bi; B-site is occupied by at least one element selected from the group consisting of Ti, V, Cr, Zr, Nb, Mo, Hf, Ta, W, Ir, and Sn; C-site is occupied by at least one element selected from the group consisting of S, Se and Te; the compounds exhibit large figure of merit so as to be preferable for thermoelectric generator/refrigerator.

MoTaIr

THERMOELECTRIC MATERIAL AND THERMOELECTRIC CONVERTING ELEMENT USING THE SAME

FIELD OF THE INVENTION

[0001] This invention relates to a thermoelectric material and a thermoelectric element and, more particularly, to a thermoelectric material in chalcogen series containing transition metal such as titanium and a thermoelectric converting element using the same.

DESCRIPTION OF THE RELATED ART

[0002] Alternative energy of fossil fuel and environmental conservation are important agenda in the world, and are discussed worldwide. In the circumstances, the thermoelectric converting technologies are attractive. The thermoelectric conversion does not produce any anti-environmental gas such as carbon dioxide gas and nitrooxides. Waste heat is reused as electric energy through the thermoelectric conversion, and the refrigerant against the environment such as freon is not required for refrigerators. Thus, the thermoelectric conversion is free from the environmental destruction, and the thermoelectric conversion is promising technologies.

[0003] The efficiency of the thermoelectric conversion is defined by the "figure of merit" ZT , and the figure of merit is expressed as

$$ZT = S^2 T / \rho \kappa \quad (1)$$

[0004] where S is Seebeck coefficient, T is temperature, ρ is the electrical resistivity and κ is the thermal conductivity. When the figure of merit increased in value, the thermoelectric converting efficiency is improved. From equation (1), it is understood that a large figure of merit is achieved by a substance which has a large Seebeck coefficient, small electrical resistivity and small thermal conductivity. The figure of merit has a certain temperature dependency unique to the thermoelectric material. For this reason, the thermoelectric materials have each temperature ranges available for applications.

[0005] Electric generators driven by steam turbines and compressor-type refrigerators are now the major thermoelectric converter. In order to achieve the thermoelectric efficiency larger than that of the electric generators/refrigerators by using the thermoelectric materials, the thermoelectric materials are to have the figure of merit ZT of the order of 3.

[0006] Even though such a large figure of merit ZT is difficult, certain thermoelectric materials are active in the relatively low temperature range, in which the steam turbines can not operate, and have a position superior to the conventional thermoelectric converters. Nevertheless, the thermoelectric materials are to exhibit the figure of merit greater than 1 for practical application.

[0007] Various non-oxide semiconductor thermoelectric materials have been proposed. Thermoelectric materials in the bismuth-tellurium series have the unique temperature range from room temperature to 400 degrees in centigrade, and exhibit good performance in the unique temperature range. Thermoelectric materials in the lead-tellurium series exhibit good performance until 700 degrees in centigrade, and silicon-germanium series exhibit good performance

until 1000 degrees in centigrade. The thermoelectric materials in the bismuth-tellurium series are used for the thermoelectric refrigeration, and the thermoelectric materials in the lead-tellurium series and silicon-germanium series are used for the thermoelectric generation.

[0008] On the other hand, $(\text{Zn}_{1-x}\text{Al}_{0.02})\text{O} \cdot \text{AB}_2\text{O}_4$, which is disclosed in Japanese Patent Application laid-open No. 7-231122, and NaCo_2O_4 are examples of the oxide thermoelectric material. A and B are metal elements, and In is contained in B site. $(\text{Zn}_{1-x}\text{Al}_{0.02})\text{O} \cdot \text{AB}_2\text{O}_4$ and NaCo_2O_4 are proposed as thermoelectric generators using a high temperature heat source of the order of 700 degrees in centigrade and thermoelectric generators active from room temperature to high temperature range. However, those thermoelectric materials exhibit the figure of merit of the order of 1.

[0009] A problem inherent in the conventional thermoelectric materials is the low conversion efficiency. The conventional energy converters are undesirable from the viewpoint of the environment and safety. The petroleum, coal, natural gas and electric power generated by the nuclear power plants will be superseded by clean energy obtained through the thermoelectric conversion. If so, there will be a great demand for thermoelectric material greater in converting efficiency than the conventional thermoelectric materials in the bismuth-tellurium series, lead-tellurium series and silicon-germanium series.

SUMMARY OF THE INVENTION

[0010] It is therefore an important object of the present invention to provide thermoelectric material, which exhibits the thermoelectric converting efficiency greater than the conventional thermoelectric materials.

[0011] It is also an important object of the present invention to provide a thermoelectric generator, which achieves a high energy converting efficiency.

[0012] It is also an important object of the present invention to provide a thermoelectric refrigerator, which achieves a high energy converting efficiency.

[0013] In accordance with one aspect of the present invention, there is provided a compound having a CdI_2 analogous layer structure and expressed by general formula of $\text{A}_x\text{BC}_{2-y}$ where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$, the A is at least one element selected from the group consisting of lithium, sodium, potassium, rubidium and cesium, the B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin, and the C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

[0014] In accordance with another aspect of the present invention, there is provided a compound having a CdI_2 analogous layer structure and expressed by general formula of $\text{A}_x\text{BC}_{2-y}$ where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$, the A is vacant, the B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin, and the C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

[0015] In accordance with yet another aspect of the present invention, there is provided a compound having a CdI_2 analogous layer structure and expressed by general formula of A_xBC_{2-y} , where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$, the A is at least one element selected from the group consisting of lithium, sodium, potassium, rubidium, cesium, magnesium, calcium, strontium, barium, titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc (Zn), zirconium, niobium, molybdenum, ruthenium, rhodium, palladium, silver, cadmium, hafnium, tantalum, tungsten, rhenium, iridium, platinum, gold, rare-earth elements containing scandium and yttrium, boron, aluminum, gallium, indium, thallium, tin, lead, antimony and bismuth, the B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin, and the C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

[0016] In accordance with still another aspect of the present invention, there is provided a thermoelectric generator comprising a first piece of thermoelectric material and a second piece of thermoelectric material different from the second thermoelectric material, the thermoelectric material having a CdI_2 analogous layer structure and expressed by general formula of A_xBC_{2-y} , where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$, in which the A is at least one element selected from the group consisting of lithium, sodium, potassium, rubidium and cesium, and in which the B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin, and in which the C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

[0017] In accordance with yet another aspect of the present invention, there is provided a thermoelectric refrigerator comprising a first piece of thermoelectric material and a second piece of thermoelectric material different from the second thermoelectric material, the thermoelectric material having a CdI_2 analogous layer structure and expressed by general formula of A_xBC_{2-y} , where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$, in which the A is at least one element selected from the group consisting of lithium, sodium, potassium, rubidium and cesium, and in which the B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin, and in which the C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Thermoelectric Material

[0018] The inventors discovered that attractive thermoelectric materials, which had a CdI_2 analogous layer structure obtained through an appropriate element substitution, intercalation and desulfurization, exhibited the electrical resistivity of the order of $1 \text{ m}\Omega\text{cm}$ and Seebeck coefficient larger than $100 \mu\text{V/K}$. The thermoelectric materials were expressed by general formula (2).



[0019] The A -site was occupied by at least one Group 1 element, i.e., lithium (Li), sodium (Na), potassium (K), rubidium (Rb) and cesium (Cs). Otherwise, the A site was a vacant site, and, accordingly, the thermoelectric material was expressed as (TiS_{2-y}) .

[0020] The inventors further discovered that the following compounds exhibited good thermoelectric properties. The compounds was expressed by the general formulae, in which part of or all of the Group 1 element or elements in the general formula (2) was replaced with at least one of the elements selected from the group consisting of Group 2 elements, i.e., magnesium (Mg), calcium (Ca), strontium (Sr) and barium (Ba), 3d-transition metals from titanium (Ti) to zinc (Zn), 4d-transition metals from zirconium (Zr) to cadmium (Cd), 5d-transition metals from hafnium (Hf) to gold (Au), rare-earth elements containing scandium (Sc) and yttrium (Y), boron (B), aluminum (Al), gallium (Ga), indium (In), thallium (Tl), tin (Sn), lead (Pb), antimony (Sb) and bismuth (Bi).

[0021] The compounds was further expressed by the general formulae, in which part of or all of titanium (Ti) is replaced with at least one element selected from the group consisting of vanadium (V), chromium (Cr), zirconium (Zr), niobium (Nb), molybdenum (Mo), hafnium (Hf), tantalum (Ta), tungsten (W), iridium (Ir) and tin (Sn).

[0022] The compound was further expressed by the general formulae, in which part of or all of sulfur (S) was replaced with at least one element selected from the group consisting of selenium (Se) and tellurium (Te).

[0023] The thermoelectric materials exhibited high energy converting efficiency, and the problem is solved.

[0024] The low electrical resistivity is derived from the fact that the CdI_2 analogous layer structure is a laminate of TiS_2 , which exhibits a relatively high electric conductivity. The TiS_2 layers are bonded by the weak van der Waals force, and, accordingly, the thermal conductivity is relatively low. Moreover, the thermal conductivity is further reduced in the presence of the element or elements intercalated into the boundaries between the layers. The compound with the CdI_2 analogous layer structure has the large Seebeck coefficient by virtue of various features such as the large degree of freedom of orbital, electron correlation and low dimensionality.

[0025] The compounds with the CdI_2 analogous layer structure which were expressed by the general formulae of A_xTiS_{2-y} where $0 \leq x \leq 2$ and $0 \leq y < 1$ have layers of hexagonal dense packing of sulfur ions, and Ti atoms occupy octahedral sites in every other sulfur layer. In other words, edge-sharing TiS_6 octahedra form infinite layers, and these layers are stacked. The TiS_6 layers are bonded each other by the weak van der Waals force, and various kinds of ions and molecules are intercalated into the van der Waals gap between the TiS_6 layers.

[0026] The general formulae are represented by the sulfur-deficient chemical composition. The sulfur deficiency is categorized into two groups. In one group, sulfur atoms are removed from the TiS_6 layers. In the other group, excess Ti atoms introduced between the TiS_6 layers. Electric-conductivity carriers are introduced by the deficiency of anion such

as sulfur, element substitution by different valence elements, and the intercalation of atoms or molecules in the van der Waals gap between the TiS_2 layers. In the TiS_2 layers, the orbitals of cations such as Ti atoms overlap directly or indirectly overlap through the p-orbitals of the anions, thus, the electrical resistivity is low.

[0027] There is not any limit on a method for introducing the carrier. One of the carrier introduction methods is to make the sulfur atoms deficient through a quenching from a high temperature or a heat treatment in reduction atmosphere created by using hydrogen gas, nitrogen gas or argon gas. Another carrier introduction method is to substitute an element with different valence elements. Yet another carrier introduction method is to intercalate atoms and/or molecules into the van der Waals gap between the TiS_2 layers. The above-described methods may be mixed or combined.

[0028] In case where the introduction of carrier is carried out by intercalating atoms into the A-site, it is preferable that at least one of the above-described elements at the A-site ranges from $0.1 < x < 0.5$. In case where the introduction of carrier is carried out by substituting the above-described element or elements except for Ti for the original element at the B-site, it is preferable that the element or elements are fallen within the range from 0.1 mole % to 10 mole % in all the elements at the B-site. In other words, at least one of the elements to occupy the B-site except Ti ranges from 0.1 mole % to 10 mole %, and the remaining B-site is to be occupied by Ti.

[0029] In case where the introduction of carrier is carried out by substituting the above-described element or elements except sulfur for the original element at the C-site, it is preferable that the element or elements are fallen within the range from 0.1 mole % to 10 mole % in all the elements at the C-site. In other words, at least one of the elements to occupy the C-site except sulfur ranges from 0.1 mole % to 10 mole %, and the remaining C-site is occupied by sulfur.

[0030] Since the TiS_2 layers are bonded by the weak van der Waals force, the electric conduction shows strong two-dimensionally nature, and Seebeck coefficient is enhanced by such a low dimensional electronic state. The orbital degeneracy takes place in the d-orbital of the cation such as Ti and the merged orbits in the octahedral structure of TiS_6 , and the entropy of the doped carrier is large. For this reason, the compounds exhibit the large Seebeck coefficient. Moreover, the cations such as Ti form a triangular lattices in the network where the ridgelines are shared among the octahedrons of TiS_6 , and the geometrical spin, orbital frustration and other electron correlation are strongly influential. This results in increase of the Seebeck coefficient.

[0031] Phonon and carrier are participated in the heat conduction. It is important to restrict the heat conduction through the phonon for high performance thermoelectric materials. Since the TiS_2 layers are bonded by the weak van der Waals force, the thermal conductivity is inherently low. The atoms, which were intercalated into the boundaries between the TiS_2 layers, not only participate in the carrier conduction but also serve as the phonon scattering centers. This results in reduction in thermal conductivity.

[0032] As described hereinbefore in detail, the compounds expressed by the general formula $\text{A}_x\text{TiS}_{2-y}$, where $0 \leq x \leq 2$ and $0 \leq y < 1$ exhibit the low electrical resistivity, low thermal

conductivity and large Seebeck coefficient by virtue of the above-described phenomena. As a result, large figure of merit zT , i.e., $S^2T/\rho\kappa$ is achieved by the compounds, and are preferable for high conversion efficiency thermoelectric elements.

[0033] The thermoelectric materials according to the present invention are produced through a process for producing ceramic such as, for example, a firing on blended powder sealed in a quartz tube. Single crystal thermoelectric material according to the present invention is obtained through a precipitation from a high temperature molten compound, zone melting or chemical transportation. A thin film of the thermoelectric material according to the present invention is formed by using a sputtering, laser light evaporation or vacuum evaporation. The metals at the A-site may be intercalated into the lattice structure through an electrochemical process or reaction with organic compound.

Thermoelectric Generator and Thermoelectric Refrigerator

[0034] The thermoelectric materials according to the present invention are available for any kind of thermoelectric generator and any kind of thermoelectric refrigerator.

EXAMPLES

[0035] The inventors investigated thermoelectric materials according to the present invention. The inventors firstly prepared powder of titanium (Ti), vanadium (V), chromium (Cr), zirconium (Zr), niobium (Nb), molybdenum (Mo), hafnium (Hf), tantalum (Ta), tungsten (W), sulfur (S), selenium (Se), tellurium (Te), lithium sulfide (Li_2S), sodium sulfide (Na_2S), potassium sulfide (K_2S), rubidium sulfide (Rb_2S), cesium sulfide (CsS), magnesium sulfide (MgS), calcium sulfide (CaS), strontium sulfide (SrS), barium sulfide (BaS), scandium (Sc), yttrium sulfide (Y_2S_3), other rare earth metal sulfides expressed as R_2S_3 where R is an rare earth element, transition metals from titanium (Ti) to zinc (Zn), zirconium (Zr) to cadmium (Cd) and hafnium (Hf) to gold (Au), boron (B), aluminum (Al), gallium (Ga), indium (In), thallium (Tl), tin (Sn), lead sulfide (PbS) and bismuth sulfide (Bi_2S_3). The inventors blended these kinds of powder in predetermined ratios, and the mixture was shaped into disks of 15 millimeters in diameter through a pressing at 1 Gpa. In order to prevent the disks from reaction with quartz, the inventors put the disks into an aluminum crucible, and, thereafter, inserted them into quartz tubes. Thus, the disks were grouped into two groups. Vacuum was developed in the quartz tubes, and the quartz tubes were sealed. The inventors gradually raised the temperature so as to prevent the disks from violent reaction. The temperature reached 440 degrees in centigrade. The disks were held at 440 degrees in centigrade for 24 hours, and, thereafter, were fired in an electric furnace at 800 degrees in centigrade for 100 hours. One of the groups was gradually cooled in the furnace. The other group was quenched by cooling the quartz tube in water. The sulfur became deficit, and the electric conductivity was observed.

[0036] The inventors produce single crystalline thermoelectric pieces through vapor phase transportation using iodine. The single crystalline thermoelectric pieces were divided into two groups, and one of the groups was subjected to desulfurization in argon atmosphere at 800 degrees in centigrade for 12 hours. Thus, the inventors prepared various kinds of samples.

[0037] The inventors analyzed the crystal structure of the samples by using an x-ray diffraction, and confirmed that the samples had the CdI_2 analogous layer structure.

[0038] Subsequently, the inventors investigated the thermoelectric properties of the samples. The inventors measured the electrical resistivity ρ , Seebeck coefficient S and thermal conductivity κ . The direct current four-probe method was used in the measurement of the electrical resistivity. The Seebeck coefficient was determined by a constant method. First, a temperature difference was given between both ends of each sample, and the thermoelectromotive force was measured. The thermal conductivity was measured by using a laser flush method. The figure of merit ZT was calculated through equation (1), i.e., $ZT = S^2 T / \rho \kappa$.

[0039] The inventors carried out experiments (1) to (79) at room temperature, i.e., 28 degrees in centigrade and experiments (80) to (158) at 700 degrees in centigrade. The samples used in experiment Nos. 1 and 80 were gradually cooled, and the thermoelectric materials were polycrystalline. The samples used in experiment Nos. 2 and 81 were quenched, and the thermoelectric materials were also polycrystalline. The samples used in experimental No. 82 were produced through the vapor phase transportation method, and the thermoelectric material was single crystalline. The samples used in experiment Nos. 4 and 83 were produced through the process same as that for the sample used in experiment No. 3, and were further desulfurized in argon atmosphere. The samples used in experiment Nos. 6, 8, 10, 85, 87 and 89 were produced through the vapor phase transportation, and the thermoelectric materials were single crystalline. The other samples were gradually cooled, and the thermoelectric materials were polycrystalline.

[0040] The composition of the samples in experiments (1) to (79) was described in Table 1, and the thermoelectric properties were shown in Table 2. Similarly, the composition of the samples in experiments (80) to (158) was described in Table 3, and the thermoelectric properties were shown in Table 4. In Tables 1 and 3, A, B, B*, C and C* represented terms "major element at A-site", "major element at B-site", "substituted element for B", "major element at C-site" and "substituted element for C", respectively. The A-site, B-site and C-site were indicative of A, B and C in general formula of $\text{A}_x\text{BC}_{2-y}$, where $0 \leq x \leq 2$ and $0 \leq y < 1$.

TABLE 1

No.	A Element/ Molar ratio	B Element/ Molar ratio	B* Element/ Molar ratio	C Element/ Molar ratio	C* Element/ Molar ratio
1	—	—	Ti	1	—
2	—	—	Ti	1	—
3	—	—	Ti	1	—
4	—	—	Ti	1	—
5	Li	0.5	Ti	1	—
6	Li	0.5	Ti	1	—
7	Na	0.5	Ti	1	—
8	Na	0.5	Ti	1	—
9	K	0.5	Ti	1	—
10	K	0.5	Ti	1	—
11	Rb	0.5	Ti	1	—
12	Cs	0.5	Ti	1	—
13	Mg	0.5	Ti	1	—
14	Ca	0.5	Ti	1	—

TABLE 1-continued

No.	A Element/ Molar ratio	B Element/ Molar ratio	B* Element/ Molar ratio	C Element/ Molar ratio	C* Element/ Molar ratio
15	Sr	0.5	Ti	1	—
16	Ba	0.5	Ti	1	—
17	Ti	0.5	Ti	1	—
18	V	0.5	Ti	1	—
19	Cr	0.5	Ti	1	—
20	Mn	0.5	Ti	1	—
21	Fe	0.5	Ti	1	—
22	Co	0.5	Ti	1	—
23	Ni	0.5	Ti	1	—
24	Cu	0.5	Ti	1	—
25	Zn	0.5	Ti	1	—
26	Zr	0.5	Ti	1	—
27	Nb	0.5	Ti	1	—
28	Mo	0.5	Ti	1	—
29	Ru	0.5	Ti	1	—
30	Rh	0.5	Ti	1	—
31	Pd	0.5	Ti	1	—
32	Ag	0.5	Ti	1	—
33	Cd	0.5	Ti	1	—
34	Hf	0.5	Ti	1	—
35	Ta	0.5	Ti	1	—
36	W	0.5	Ti	1	—
37	Re	0.5	Ti	1	—
38	Ir	0.5	Ti	1	—
39	Pt	0.5	Ti	1	—
40	Au	0.5	Ti	1	—
41	Sc	0.5	Ti	1	—
42	Y	0.5	Ti	1	—
43	La	0.5	Ti	1	—
44	Ce	0.5	Ti	1	—
45	Nd	0.5	Ti	1	—
46	Pr	0.5	Ti	1	—
47	Sm	0.5	Ti	1	—
48	Eu	0.5	Ti	1	—
49	Gd	0.5	Ti	1	—
50	Tb	0.5	Ti	1	—
51	Dy	0.5	Ti	1	—
52	Ho	0.5	Ti	1	—
53	Er	0.5	Ti	1	—
54	Tm	0.5	Ti	1	—
55	Yb	0.5	Ti	1	—
56	Lu	0.5	Ti	1	—
57	B	0.5	Ti	1	—
58	Al	0.5	Ti	1	—
59	Ga	0.5	Ti	1	—
60	In	0.5	Ti	1	—
61	Tl	0.5	Ti	1	—
62	Sb	0.5	Ti	1	—
63	Pb	0.5	Ti	1	—
64	Sb	0.5	Ti	1	—
65	Bi	0.5	Ti	1	—
66	—	—	Ti	0.9	V
67	—	—	Ti	0.9	Cr
68	—	—	Ti	0.9	Zr
69	—	—	Ti	0.9	Nb
70	—	—	Ti	0.9	Mo
71	—	—	Ti	0.9	Hf
72	—	—	Ti	0.9	Ta
73	—	—	Ti	0.9	W
74	—	—	Ti	0.9	Ir
75	—	—	Ti	0.9	Sr
76	—	—	Ti	1	—
77	—	—	Ti	1	—
78	—	—	Ti	1	—
79	—	—	Ti	1	—

[0041]

TABLE 2

No.	Seebeck Coefficient $\mu\text{V/K}^\circ$	Electrical Resistivity $\text{m}\Omega\text{ cm}$	Thermal Conductivity $\text{mW/K}^\circ\text{ cm}$	Figure of Merit
1	-200	0.8	10	1.50
2	-180	0.7	10	1.39
3	-170	0.1	30	2.89
4	-160	0.08	35	2.74
5	-185	0.82	11	1.14
6	-139	0.07	28	2.96
7	-197	0.86	12	1.13
8	-141	0.08	25	2.98
9	-193	0.87	10	1.28
10	-144	0.09	24	2.88
11	-196	0.87	11	1.20
12	-195	0.87	11	1.19
13	-194	0.87	11	1.18
14	-195	0.87	12	1.09
15	-198	0.87	11	1.23
16	-200	0.9	11	1.21
17	-199	0.82	12	1.21
18	-197	0.84	11	1.26
19	-196	0.85	10	1.36
20	-196	0.87	11	1.20
21	-196	0.84	11	1.25
22	-196	0.86	12	1.12
23	-194	0.85	12	1.11
24	-196	0.87	11	1.20
25	-196	0.87	11	1.20
26	-194	0.82	12	1.15
27	-195	0.87	11	1.19
28	-196	0.87	12	1.10
29	-194	0.85	11	1.21
30	-196	0.87	11	1.20
31	-193	0.84	11	1.21
32	-196	0.87	12	1.10
33	-189	0.83	12	1.08
34	-184	0.8	11	1.15
35	-187	0.79	12	1.11
36	-188	0.8	11	1.20
37	-190	0.83	12	1.09
38	-191	0.84	12	1.09
39	-188	0.86	12	1.03
40	-192	0.87	12	1.06
41	-196	0.86	12	1.12
42	-189	0.88	11	1.11
43	-192	0.87	10	1.27
44	-198	0.86	13	1.05
45	-190	0.87	10	1.24
46	-191	0.87	10	1.26
47	-188	0.87	11	1.11
48	-192	0.87	12	1.06
49	-190	0.83	12	1.09
50	-194	0.87	12	1.08
51	-193	0.87	12	1.07
52	-190	0.81	12	1.11
53	-188	0.87	10	1.22
54	-187	0.87	10	1.21
55	-190	0.87	11	1.13
56	-194	0.84	12	1.12
57	-188	0.8	12	1.10
58	-187	0.87	11	1.10
59	-189	0.79	12	1.13
60	-184	0.8	10	1.27
61	-194	0.87	12	1.08
62	-196	0.77	13	1.15
63	-195	0.82	12	1.16
64	-197	0.87	12	1.12
65	-193	0.85	12	1.10
66	-192	0.87	11	1.16
67	-194	0.87	11	1.18
68	-188	0.76	12	1.16
69	-194	0.79	12	1.19
70	-192	0.84	12	1.10

TABLE 2-continued

No.	Seebeck Coefficient $\mu\text{V/K}^\circ$	Electrical Resistivity $\text{m}\Omega\text{ cm}$	Thermal Conductivity $\text{mW/K}^\circ\text{ cm}$	Figure of Merit
71	-192	0.87	10	1.27
72	-194	0.83	12	1.13
73	-196	0.87	12	1.10
74	-198	0.87	12	1.13
75	-196	0.87	10	1.32
76	-195	0.87	10	1.31
77	-193	0.85	10	1.31
78	-197	0.86	10	1.35
79	-192	0.84	10	1.32

[0042]

TABLE 3

No.	A Element/ Molar ratio	B Element/ Molar ratio	B* Element/ Molar ratio	C Element/ Molar ratio	C* Element/ Molar ratio
80	—	—	Ti 1	—	—
81	—	—	Ti 1	—	—
82	—	—	Ti 1	—	—
83	—	—	Ti 1	—	—
84	Li 0.5	Ti 1	—	S 1	—
85	Li 0.5	Ti 1	—	S 1	—
86	Na 0.5	Ti 1	—	S 1	—
87	Na 0.5	Ti 1	—	S 1	—
88	K 0.5	Ti 1	—	S 1	—
89	K 0.5	Ti 1	—	S 1	—
90	Rb 0.5	Ti 1	—	S 1	—
91	Cs 0.5	Ti 1	—	S 1	—
92	Mg 0.5	Ti 1	—	S 1	—
93	Ca 0.5	Ti 1	—	S 1	—
94	Sr 0.5	Ti 1	—	S 1	—
95	Ba 0.5	Ti 1	—	S 1	—
96	Ti 0.5	Ti 1	—	S 1	—
97	V 0.5	Ti 1	—	S 1	—
98	Cr 0.5	Ti 1	—	S 1	—
99	Mn 0.5	Ti 1	—	S 1	—
100	Fe 0.5	Ti 1	—	S 1	—
101	Cu 0.5	Ti 1	—	S 1	—
102	Ni 0.5	Ti 1	—	S 1	—
103	Cu 0.5	Ti 1	—	S 1	—
104	Zn 0.5	Ti 1	—	S 1	—
105	Zr 0.5	Ti 1	—	S 1	—
106	Nb 0.5	Ti 1	—	S 1	—
107	Mo 0.5	Ti 1	—	S 1	—
108	Ru 0.5	Ti 1	—	S 1	—
109	Rh 0.5	Ti 1	—	S 1	—
110	Pd 0.5	Ti 1	—	S 1	—
111	Ag 0.5	Ti 1	—	S 1	—
112	Cd 0.5	Ti 1	—	S 1	—
113	Hf 0.5	Ti 1	—	S 1	—
114	Ta 0.5	Ti 1	—	S 1	—
115	W 0.5	Ti 1	—	S 1	—
116	Re 0.5	Ti 1	—	S 1	—
117	Ir 0.5	Ti 1	—	S 1	—
118	Pt 0.5	Ti 1	—	S 1	—
119	Au 0.5	Ti 1	—	S 1	—
120	Sc 0.5	Ti 1	—	S 1	—
121	Y 0.5	Ti 1	—	S 1	—
122	La 0.5	Ti 1	—	S 1	—
123	Ce 0.5	Ti 1	—	S 1	—
124	Nd 0.5	Ti 1	—	S 1	—
125	Pr 0.5	Ti 1	—	S 1	—
126	Sm 0.5	Ti 1	—	S 1	—
127	Eu 0.5	Ti 1	—	S 1	—
128	Gd 0.5	Ti 1	—	S 1	—
129	Tb 0.5	Ti 1	—	S 1	—

TABLE 3-continued

No.	A Element/ Molar ratio	B Element/ Molar ratio	B* Element/ Molar ratio	C Element/ Molar ratio	C* Element/ Molar ratio
130	Dy 0.5	Ti 1	—	S 1	—
131	Ho 0.5	Ti 1	—	S 1	—
132	Er 0.5	Ti 1	—	S 1	—
133	Tm 0.5	Ti 1	—	S 1	—
134	Yb 0.5	Ti 1	—	S 1	—
135	Lu 0.5	Ti 1	—	S 1	—
136	B 0.5	Ti 1	—	S 1	—
137	Al 0.5	Ti 1	—	S 1	—
138	Ga 0.5	Ti 1	—	S 1	—
139	In 0.5	Ti 1	—	S 1	—
140	Tl 0.5	Ti 1	—	S 1	—
141	Sa 0.5	Ti 1	—	S 1	—
142	Pb 0.5	Ti 1	—	S 1	—
143	Sb 0.5	Ti 1	—	S 1	—
144	Bi 0.5	Ti 1	—	S 1	—
145	—	Ti 0.9	V 0.1	S 1	—
146	—	Ti 0.9	Cr 0.1	S 1	—
147	—	Ti 0.9	Zr 0.1	S 1	—
148	—	Ti 0.9	Nb 0.1	S 1	—
149	—	Ti 0.9	Mo 0.1	S 1	—
150	—	Ti 0.9	Hf 0.1	S 1	—
151	—	Ti 0.9	Ta 0.1	S 1	—
152	—	Ti 0.9	W 0.1	S 1	—
153	—	Ti 0.9	Ir 0.1	S 1	—
154	—	Ti 0.9	Sn 0.1	S 1	—
155	—	Ti 1	—	S 0.9	Se 0.1
156	—	Ti 1	—	S 0	Se 1
157	—	Ti 1	—	S 0.9	Te 0.1
158	—	Ti 1	—	S 0	Te 1

[0043]

TABLE 4

No.	Seebeck Coefficient $\mu\text{V/K}^\circ$	Electrical Resistivity $\text{m}\Omega\text{ cm}$	Thermal Conductivity $\text{mW/K}^\circ\text{ cm}$	Figure of Merit
80	-210	1	15	2.86
81	-200	0.9	17	2.54
82	-195	0.3	32	3.85
83	-190	0.28	33	3.80
84	-204	1.2	16	2.11
85	-165	0.24	28	3.94
86	-205	1	18	2.27
87	-165	0.28	27	3.50
88	-203	1.1	16	2.28
89	-167	0.29	26	3.60
90	-202	1.3	19	1.61
91	-204	1.3	17	1.83
92	-206	1.2	18	1.91
93	-204	1.2	18	1.87
94	-202	1.1	18	2.01
95	-200	1.2	18	1.80
96	-199	1.2	17	1.89
97	-197	1.2	18	1.75
98	-196	1.2	17	1.83
99	-196	1.2	18	1.73
100	-201	1.2	18	1.82
101	-203	1.2	17	1.97
102	-201	1.2	18	1.82
103	-200	1.2	18	1.80
104	-205	1.2	19	1.79
105	-201	1.2	17	1.93
106	-200	1.2	17	1.91
107	-202	1.2	17	1.95
108	-203	1.2	18	1.86
109	-210	1.2	19	1.88

TABLE 4-continued

No.	Seebeck Coefficient $\mu\text{V/K}^\circ$	Electrical Resistivity $\text{m}\Omega\text{ cm}$	Thermal Conductivity $\text{mW/K}^\circ\text{ cm}$	Figure of Merit
110	-209	1.2	19	1.86
111	-203	1.1	19	1.92
112	-205	1.2	18	1.89
113	-206	1.2	18	1.91
114	-200	1.2	17	1.91
115	-201	1.1	19	1.88
116	-203	1.2	18	1.86
117	-205	1.2	18	1.89
118	-200	1.1	18	1.97
119	-206	1.2	19	1.81
120	-210	1.2	17	2.10
121	-208	1.2	17	2.06
122	-207	1.2	17	2.04
123	-203	1.2	18	1.86
124	-205	1.2	18	1.89
125	-200	1	18	2.16
126	-206	1.2	19	1.81
127	-206	1.2	18	1.91
128	-205	1.2	17	2.00
129	-206	1.2	17	2.02
130	-207	1.2	18	1.93
131	-203	1	19	2.11
132	-202	1.2	18	1.84
133	-205	1.2	18	1.89
134	-208	1.2	18	1.95
135	-206	1.2	18	1.91
136	-203	1.1	17	2.14
137	-201	1	18	2.18
138	-208	1.2	18	1.95
139	-210	1.2	18	1.99
140	-200	1	19	2.05
141	-210	1.2	18	1.99
142	-209	1.2	18	1.97
143	-205	1.2	18	1.89
144	-204	1.2	17	1.98
145	-210	1.2	17	2.10
146	-211	1.2	18	2.01
147	-205	1.2	18	1.89
148	-208	1.2	19	1.85
149	-204	1.2	18	1.87
150	-207	1.2	17	2.04
151	-209	1.05	18	2.25
152	-204	1.2	16	2.11
153	-207	1.1	16	2.37
154	-206	1.2	17	2.02
155	-226	1.2	19	2.18
156	-220	1	20	2.35
157	-220	1.3	17	2.13
158	-215	1	19	2.37

[0044] From Tables 2 and 4, it was understood that the CdI_2 analogous layer structure compounds, which were expressed by the general formula of $\text{A}_x\text{BC}_{2-y}$ ($0 \leq x \leq 2$ and $0 \leq y < 1$), exhibited the figure of merit better than that of the prior art thermoelectric materials at room temperature and 700 degrees in centigrade.

[0045] As will be appreciated from the foregoing description, the thermoelectric material according to the present invention exhibit the large figure of merit, and, accordingly, are available for the thermoelectric generators and thermoelectric refrigerators. The thermoelectric generators and thermoelectric refrigerators achieve high energy converting efficiency by virtue of the large figure of merit of the thermoelectric materials according to the present invention.

[0046] Although particular embodiments of the present invention have been shown and described, it will be apparent

to those skilled in the art that various changes and modifications may be made without departing from the spirit and scope of the present invention.

What is claimed is:

1. A compound having a CdI_2 analogous layer structure and expressed by general formula of



where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$,

in which said A is at least one element selected from the group consisting of lithium, sodium, potassium, rubidium and cesium,

and in which said B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin,

and in which said C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

2. The compound as set forth in claim 1, in which said at least one element occupying at said A is totally replaced with at least one element selected from the group consisting of magnesium, calcium, strontium, barium, titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc (Zn), zirconium, niobium, molybdenum, ruthenium, rhodium, palladium, silver, cadmium, hafnium, tantalum, tungsten, rhenium, iridium, platinum, gold, rare-earth elements containing scandium and yttrium, boron, aluminum, gallium, indium, thallium, tin, lead, antimony and bismuth.

3. The compound as set forth in claim 1, in which said at least one element occupying at said A is partially replaced with at least one element selected from the group consisting of magnesium, calcium, strontium, barium, titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc (Zn), zirconium, niobium, molybdenum, ruthenium, rhodium, palladium, silver, cadmium, hafnium, tantalum, tungsten, rhenium, iridium, platinum, gold, rare-earth elements containing scandium and yttrium, boron, aluminum, gallium, indium, thallium, tin, lead, antimony and bismuth.

4. The compound as set forth in claim 1, in which said B and said C are titanium and sulfur, respectively.

5. A compound having a CdI_2 analogous layer structure and expressed by general formula of



where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$,

in which said A is vacant,

and in which said B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin,

and in which said C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

6. The compound as set forth in claim 5, in which said B and said C are titanium and sulfur, respectively.

7. A compound having a CdI_2 analogous layer structure and expressed by general formula of



where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$,

in which said A is at least one element selected from the group consisting of lithium, sodium, potassium, rubidium, cesium, magnesium, calcium, strontium, barium, titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc (Zn), zirconium, niobium, molybdenum, ruthenium, rhodium, palladium, silver, cadmium, hafnium, tantalum, tungsten, rhenium, iridium, platinum, gold, rare-earth elements containing scandium and yttrium, boron, aluminum, gallium, indium, thallium, tin, lead, antimony and bismuth,

and in which said B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin,

and in which said C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

8. The compound as set forth in claim 7, in which said B and said C are titanium and sulfur, respectively.

9. A thermoelectric generator comprising a first piece of thermoelectric material and a second piece of thermoelectric material different from said second thermoelectric material, said thermoelectric material having a CdI_2 analogous layer structure and expressed by general formula of



where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$,

in which said A is at least one element selected from the group consisting of lithium, sodium, potassium, rubidium and cesium,

and in which said B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin,

and in which said C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

10. The thermoelectric generator as set forth in claim 9, in which said at least one element occupying at said A is totally replaced with at least one element selected from the group consisting of magnesium, calcium, strontium, barium, titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc (Zn), zirconium, niobium, molybdenum, ruthenium, rhodium, palladium, silver, cadmium, hafnium, tantalum, tungsten, rhenium, iridium, platinum, gold, rare-earth elements containing scandium and yttrium, boron, aluminum, gallium, indium, thallium, tin, lead, antimony and bismuth.

11. A thermoelectric refrigerator comprising a first piece of thermoelectric material and a second piece of thermoelectric material different from said second thermoelectric material, said thermoelectric material having a CdI_2 analogous layer structure and expressed by general formula of



where x is fallen within the range of $0 \leq x \leq 2$ and y is fallen within the range of $0 \leq y < 1$,

in which said A is at least one element selected from the group consisting of lithium, sodium, potassium, rubidium and cesium,

and in which said B is at least one element selected from the group consisting of titanium, vanadium, chromium, zirconium, niobium, molybdenum, hafnium, tantalum, tungsten, iridium and tin,

RD 236028

and in which said C is at least one element selected from the group consisting of sulfur, selenium and tellurium.

12. The thermoelectric refrigerator as set forth in claim 11, in which said at least one element occupying at said A is totally replaced with at least one element selected from the group consisting of magnesium, calcium, strontium, barium, titanium, vanadium, chromium, manganese, iron, cobalt,

nickel, copper, zinc (Zn), zirconium, niobium, molybdenum, ruthenium, rhodium, palladium, silver, cadmium, hafnium, tantalum, tungsten, rhenium, iridium, platinum, gold, rare-earth elements containing scandium and yttrium, boron, aluminum, gallium, indium, thallium, tin, lead, antimony and bismuth.

* * * * *